


Slip test results

DBSSTLHTFN

Stainless Steel Hounds Teeth Directional Bars

SLIP RESISTANCE TEST REPORT		OPUS	
Project :	Slip Resistance Investigation		
Location of Test :	Auckland Laboratory		
Client :	CMT Group NZ Ltd - Total Tactilez		
Slider type :	FOUR-S, Prepared on P 400 (or equivalent) sand paper & Wet Lapping film.		
Specimen Description :	TacStud Stainless Steel Studs with No lip (hounds teeth design)		
Cleaning Procedure :	Wet Brush	Project Number :	1-LA410.00
Test Type :	Unfixed	Lab Ref. Number :	AL2927/7
Air Temp at Test (°C) :	19	Client Ref. Number :	-
SLIP RESISTANCE TEST RESULTS			
Test № :	Test Direction :	Mean BPN :	Mean Coefficient of Friction*
1	N/A	60	0.67
2		56	0.61
3		59	0.65
4		58	0.64
5		61	0.68
Average (SRV) :		59	0.65
Classification of pedestrian surface material in accordance with table 2, AS 4586:2013 :			P5
TEST METHOD			
Tests were carried out in accordance with Appendix A, AS 4586:2013, the classification is based on a test in the wet condition.			
*Coefficient of friction obtained from: AS/NZS 3661.1 : 1993 Slip Resistance of Pedestrian Surfaces.			
SAMPLE TESTED			
			
Tested By :	OPUS - G. Sandford		
Designation :	Civil Engineering Technician		
Date Tested :	10/08/18		
LAF026 (08/17)			Page 1 of 1
OPUS International Consultants Ltd. Auckland Laboratory Quality Management Systems Certified to ISO 9001	7a Ride Way, Albany Private Bag 101982, NS Mail Centre, North Shore City 0745, New Zealand	Telephone +64 9 415 4660 Facsimile +64 9 415 4661 Website www.opus.co.nz	